

Aleación	Especificación	C	Mn	Si	Cr	Mo	W	Co	P (máx.)	S (máx.)	V	Fe	Other
<b>A-2</b>	ASTM A 597 CA-2	.95-1.05	0.75	1.5	4.75-5.50	.90-1.40			0.03	0.03	20-.50	Bal.	
<b>D-2</b>	ASTM A 597 CD-2	1.40-1.60	1	1.5	11.00-13.00	.70-1.20		.70-1.00	0.03	0.03	.40-1.00	Bal.	
<b>D-5</b>	ASTM A 597 CD-5	1.35-1.60	0.75	1.5	11.00-13.00	.70-1.20		2.50-3.50	0.03	0.03	.35- .55	Bal.	Ni .40-.60
<b>H-11</b>	IC CH-11	.30-.40	0.75	.95-1.15	4.60-5.40	1.20-1.60			0.025	0.025	.30- .50	Bal.	
<b>H-12</b>	ASTM A 597 CH-12	.30-.40	0.75	1.5	4.75-5.75	1.25-1.75	1.00-1.70		0.03	0.03	.20- .50	Bal.	
<b>H-13</b>	ASTM A 597 CH-13	.30- .42	0.75	1.5	4.75-5.75	1.25-1.75			0.03	0.03	.75-1.20	Bal.	
<b>M-2</b>	ASTM A 597 CM-2	.78- .88	0.75	1	3.75-4.50	4.50-5.50	5.50-6.75	0.25	0.03	0.03	1.25-2.20	Bal.	Ni .25 Max
<b>M-4</b>	IC CM-4	1.25-1.35	0.75	1	3.75-4.50	4.50-5.50	5.20-6.20		0.025	0.025	3.60-4.40	Bal.	
<b>O-1</b>	ASTM A 597 CO-1	.85-1.00	1.00-1.30	1.5	.40-1.00		.40- .60		0.03	0.03	0.3	Bal.	
<b>O-2</b>	IC CO-2	.85- .95	1.50-1.80	1	0.4	0.3			0.025	0.025	0.3	Bal.	
<b>S-2</b>	IC CS-2	.45- .55	0.75	.90-1.20		.40- .60			0.025	0.025	0.3	Bal.	
<b>S-5</b>	ASTM A 597 CS-5	.50- .65	.60-1.00	1.75-2.25	0.35	.20- .80			0.03	0.03	0.35	Bal.	
<b>S-7</b>	ASTM A 597 CS-7	.45- .55	.40- .80	.60-1.00	3.00-3.50	1.20-1.60			0.03	0.03		Bal.	
<b>T-1</b>	IC CT-1	.65- .75	0.75	1	3.75-4.50		17.25-18.75		0.025	0.025	.90-1.30	Bal.	